KLEENSCREEN BLACKOUT SOLAR SCREEN





Test Report No. SDHL1709020432HI Date: Oct.18, 2017 Page 1 of 2

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description : KLEENSCREEN BLACKOUT SGS Ref. No. : GZAFN1709016923P001

Sample Receiving Date : Sep.28, 2017

Test Performing Date : Sep.28, 2017 to Oct.17, 2017

Test Result Summary

Test(s) Requested	Result(s)	Comments
Assessment of Antimicrobial activity With reference to ASTM E 2180-07 (Reapproved 2012)	Please refer to the following page(s)	/
For further details, please refer to the following page(s)		

Signed for and on behalf of Shunde Branch SGS-CSTC Co., Ltd.

Peter Zhao Approved signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions or Service printe overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.appa-rems-and-Condi

Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 830' 1443, or email: CN.Doccheck@sgs.com

| 15;「Paiding,Einyaen Industrial Part/Lot | Shurthe Shaft Routly | Shaft Routly

Member of the SGS Group (SGS SA)

KLEENSCREEN BLACKOUT SOLAR SCREEN





Test Report No. SDHL1709020432HI Date: Oct.18, 2017 Page 2 of 2

TEST RESULT(S):

Assessment of Antimicrobial activity

Test method: With reference to ASTM E 2180-07 (Reapproved 2012)

Test organisms: Staphylococcus aureus ATCC 6538, Klebsiella pneumoniae ATCC 4352

Name of test bacteria (Strain number)	Concentration of bacteria (cells/mL)	/	The antilog of the geometric mean of the number of organisms recovered from "0h" (cfu/mL)	The antilog of the geometric mean of the number of organisms recovered from "24h" (cfu/mL)	Reduction (%)
Staphylococcus aureus ATCC 6538	1.9 x 10 ⁶	Sample	/	5.0 x 10 ¹	> 99.9
		Control Sample	8.9 x 10 ⁵	2.1 x 10 ⁶	
Klebsiella		Sample	/	5.0 x 10 ¹	
pneumoniae ATCC 4352	2.9 x 10 ⁶	Control Sample	1.3 x 10 ⁶	5.5 x 10 ⁶	> 99.9

Remark: The control sample is plastic film without antimicrobial activity, provided by SGS laboratory.

SAMPLE DESCRIPTION: Fabric

Photo Appendix:



Remark: This test was subcontracted to SGS-CSTC Standards Technical Services Co.,Ltd. Guangzhou Branch.

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sps.com/en/Terms-and-Conditions.aspx.and-conditions for subject to Terms and Conditions for Electronic Documents at http://www.sps.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document son experience and the subject of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

1443, or email: CN.Doccheck@sgs.com

| 15;「Paiding,Einyaen Industrial Part/Lot | Shurthe Shaft Routly | Shaft Routly

Member of the SGS Group (SGS SA)