UNO BLACKOUT

4-Ply Vinyl Blackout

Vinyl blackout roller shades are a staple product among shade makers. As one of the most versatile and affordable options for roller shades, our Uno Blackout is a 4-ply vinyl blackout that offers a semi-matte, plain-weave texture in a selection of timeless colorways. It is easy to clean, moisture resistant, flame retardant, and readily available in multiple cost-effective widths.

SPECIFICATIONS

 Product Type: Vinyl Blackout Applications: Roller Shades, Panel Blinds Fire Retardant: NFPA 701-2019 Small Scale Test Standard Roll Length: 30 yards 	 Widths: White 72", 100", 118" Linen 72", 100" Champagne 72", 100" Fawn 72", 100" Grey 72", 100", 118" Black 72", 118" 	WHITE	LINEN
 Composition: 4-Ply PVC Laminated Fiberglass (75% PVC, 25% Fiberglass) Weave: Plain Openness Factor: 0% Thickness: 0.0138 in ± 0.0004 in Weight: 13.27 oz/yd² ± 0.35 oz 	 Cutting: Ultrasonic, Crush, Cold Welding/Bonding Tape: No Railroading: Not recommended; subject to testing. Warranty: 5 years 	CHAMPAGNE	FAWN
 ✓ UV Resistant ✓ Printable ✓ Lead Free Color Fastness: Grade 5-6, Tested to ISO 105 B0 Thread Count: Warp : 40 yarns /in; Weft: 24 yarns /in (100') Warp: 32 yarns /in; Weft: 20 yarns /in (Only) 	02-2014 ' and up)	GREY	BLACK

LINEN

FAWN

TECHNICAL SPECIFICATIONS

Composition 100% PES Weight 350 g/m² (±5%) | 10.3 oz/yd² (±5%) Thickness 0.46 mm (±5%) | 0.018 in (±5%) Roll Width 3.0 m | 118 in Roll Length 30 m | 32.81 yd UV Blockage 100% Light Fastness <6 Xenotest Grade Mesh (in) Wrap: 101 | Fill: 56 Flame Retardant NFPA 701

CLEANING AND MAINTENANCE

Vacuum clean for regular maintenance. Do not use soap solutions nor a damp cloth Do not wash Do not wring dry. Do not bleach. Do not dry clean nor use steam cleaning.



OPTICAL PROPERTIES UV Blockage 100%

CERTIFICATES



- Warp : 40 yarns /in; Weft: 24 yarns /in (100" and up)
- Warp: 32 yarns /in; Weft: 20 yarns /in (Only for 72")
- Tensile Strength: Warp 255.8 lbf, Weft 289.8 lbf, Tested to ASTM D5034-2009(2013)
- Tearing Strength: Including Warp & Filling: Warp 11.8 lbf / Weft Over 14.0 lbf, Tested to ASTM D1424-2009(2013)
- Adhesion Strength: Length 3.7 lbf/inch, Width 3.7 lbf/inch, Tested to ASTM D751-2006, Tensile testing Machine, CRE

• Care & Cleaning Instructions: Clean with warm water. Material can be washed on both sides with mild 5% detergent solution.

• Color variances may occur between fabric production batches. These variances are within industry tolerances, kindly check fabric prior to cutting.





Shades by Matiss New York | Chicago | Los Angeles T.800-493-2040 | info@shadesbymatiss.com