

3000 HT

3000 HT SOLAR SHADE FABRIC 3% - 5% OPENNESS

 **SHADES BY MATISS**



The broken twill weave of the 3000 HT offers customers a solution where white is always facing out, giving the fabric superior reflective properties, providing improved heat control and without limiting the color of their interior fabric to white.

3000 HT

SOLAR SHADE FABRIC 3% - 5% OPENNESS

SPECIFICATIONS

Specification	3000 HT 3%	3000 HT 5%
Composition	25% Polyester, 75% PVC	25% Polyester, 75% PVC
Openness	3%	5%
Width(s)	98.4" (2.5m)	98.4" (2.5m)
Length	33 yd/roll (30m)	33 yd/roll (30m)
Weight	12.24 oz/yd ² (415 g/m ²)	11.65 oz/yd ² (395 g/m ²)
Thickness	0.024 in (0.60mm)	0.026 in (0.66mm)
Fire Classification	NFPA 701, M2, BS 5867 Type B, CA Title 19	NFPA 701, M2, BS 5867 Type B, CA Title 19
Fungal/Bacterial Resistance	ASTM E2180, G21, G22	ASTM E2180, G21, G22
Acoustical Performance	NRC 0.15 SAA 0.15	Negligible
Railroadable	No	No

Fabrication Methods

Cutting: Knife, Crush, Ultrasonic

Welding: 248°F (120°C) to 284°F (140°C), Test First

Care & Cleaning

Lightly vacuum or wipe with dry cloth to remove dust. Spot clean with clean white pencil eraser or gently wipe with warm soapy water and damp sponge. If wet, leave shade down to dry completely. Avoid solvents or test them in inconspicuous area first.

