

Product Specifications Sheet







E Screen™ 1% KOOLBLACE

Specifications

Product Category: High Performance

Openness Factor: 1%

UV Blockage: Approximately 99% Fabric Style: Basketweave

Item #: 007701

Composition: 36% fiberglass / 64% vinyl

Standard Packaging: Rolls of 30 ly (27 lm)

Width: 98" (250 cm), 122" (310 cm)
Weight: 12.95 oz / yd2 (439 g / m2) ± 5%

Thickness: 0.021" (0.53 mm) ± 5%

Fenestration Data

| | Fabric Properties | | | | | | Fabric & Glass | | | | |
|--------|---------------------|-----------|-------------|--------|--------|---------|----------------|--------------------|----------|-------------|----------|
| | | Thermal | | | | Optical | | Commercial | | Residential | |
| Color# | Color Name | Rs IR (%) | Total Solar | | | Rv (%) | Tv (%) | SHGC % Improvement | | SHGC | |
| | | | Rs (%) | As (%) | Ts (%) | NV (70) | IV (70) | Interior | Exterior | Interior | Exterior |
| 035035 | Charcoal/Charcoal | 64 | 35 | 53 | 12 | 9 | 2 | 18 | 82 | 0.48 | 0.14 |
| 00K122 | Charcoal/Grey-Stone | 63 | 38 | 50 | 12 | 17 | 3 | 24 | 82 | 0.47 | 0.14 |
| 035131 | Charcoal/Grey | 67 | 40 | 49 | 11 | 16 | 2 | 24 | 84 | 0.46 | 0.13 |
| 035032 | Charcoal/Cocoa | 64 | 36 | 52 | 12 | 11 | 2 | 21 | 82 | 0.48 | 0.14 |
| 035071 | Charcoal/Apricot | 62 | 39 | 47 | 14 | 19 | 3 | 24 | 82 | 0.46 | 0.15 |

The fabric performance tests were conducted in accordance with ASTM E891 & ASTM E903-96: Total Solar Transmittance (Ts), Total Solar Reflectance (Rs), Solar Reflectance in Infrared (Rs IR), Total Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory Window 7.3 NFRC certified software. SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm / vs with 16 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3mm clear glass / 1/2" air / 3mm clear glass. Results for SHGC were obtained using the center of glass. Acoustical performance was tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: www.mermetusa.com.

Fabrication Methods:

Cutting: cold, ultrasonic or crush

Welding: radio frequency, high frequency, impulse,

hot air, wedge

Fire Classifications:

NFPA 701-10 TM#1, California U.S. Title 19

CAN/ULC-S109-03 Small Flame Test

Bacterial and Fungal Resistance: ASTM E2180, ASTM G21

Environmental Benefits:

RoHS - Lead Free

Acoustical Performance: NRC: 0.45, SAA: 0.46

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

5970 N. Main Street • Cowpens, SC 29330 Sales Department: Ph (866) 902-9647

info@mermetusa.com

