

Product Specifications Sheet







E Screen Chroma™

Specifications

Product Category: High Performance Composition: 36% fiberglass / 64% vinyl

Ultra-fine layer of aluminum

Openness Factor: 3% Standard Packaging: Rolls of 33 ly (30 lm) **UV Blockage:** Approximately 97%

Width: 94.5" (240 cm)

 $11.92 \text{ oz / yd2 } (404 \text{ g / m2}) \pm 5\%$ Fabric Style: Basketweave Weight: Item #: 037503

Thickness: 0.020" (0.50 mm) ± 5%

Fenestration Data

			Fabric Properties					Fabric & Glass		
			Thermal			Optical		Commercial	Residential	Emissivity
Color#	Color Name	Side*	Total Solar			Rv (%)	Tv (%)	SHGC %	SHGC	Emissivity
			Rs (%)	As (%)	Ts (%)	INV (70)	1 V (70)	Improvement	31100	
002020	White/Linen	street	81	16	3	79	3	63	0.23	0.17
		room	67	30	3	71	2	55	0.27	0.87
002002	White/White	street	82	15	3	79	3	63	0.23	0.15
		room	74	23	3	79	3	63	0.23	0.86
002007	White/Pearl	street	80	17	3	78	3	61	0.21	0.16
		room	58	39	3	62	3	50	0.32	0.86
030007	Charcoal/Pearl	street	82	14	4	79	4	63	0.20	0.13
		room	11	86	3	12	3	21	0.55	0.87
030030	Charcoal/Charcoal	street	81	16	3	78	3	61	0.21	0.15
		room	4	93	3	5	3	16	0.57	0.87

^{*}Room side: identified by the color side; Street side: identified by the aluminum coated side

The fabric performance tests were conducted in accordance with ASTM E891 & ASTM E903-96: Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory Window NFRC certified softw SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm / ½" air / 6 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3mm clear glass / 1/2" air / 3mm clear glass. Results for SHGC were obtained using the center of glass. Emissivity was tested in accordance with ASTM C1371. Acoustical performance was tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: www.mermetusa.com

Fabrication Methods: Fire Classifications: **Environmental Benefits:**

Cutting: cold, ultrasonic or crush NFPA 701-10 TM#1, California U.S. Title 19 RoHS - Lead Free

Welding: do not use radio frequency or high frequency welding CAN/ULC-S109 Small & Large scale machines. Heat impulse welding equipment is recommended. **Acoustical Performance: Bacterial and Fungal Resistance:**

ASTM E2180, ASTM G21 NRC: 0.30, SAA: 0.28

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

Care & Handling

Storage: fabric needs to be stored in cardboard tubes to prevent bowing of the fabric or the inner core that the fabric is wrapped around.

Transportation: fabric should be shipped in the same cardboard tubes, or carefully bulk packaged to avoid crushing of the fabric.

Handling: fabric should always remain in its native outer packaging during storage, and/or moving. The fabric should be carried with an even distribution across the length of the roll. Unlike most metalized fabrics, cotton gloves are not required for handling.

Placement: There needs to be at least 1" between finished shade and glass. Skylights require greater space between finished shade and glass to avoid thermal heat buildup.

5970 N. Main Street • Cowpens, SC 29330 Sales Department: Ph (866) 902-9647

info@mermetusa.com

05.19 v2 www.mermetusa.com

