

# OMNIASCREEN

VEROSOL HIGH PERFORMANCE FABRICS



TEXTSTYLE




96-D Allen Boulevard  
 Farmingdale, New York 11735-5626 USA  
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
 e-mail: testing@govmark.com


Page 1

Received:03/24/2016	Completed:03/24/2016	Letter: Y	BG	P.O.#:	Test Report #:	3-12415-0-
<b>Client's Identification</b>	Style: OmniaScreen. Composition: 75% PVC, 25% Polyester. Weight: 440 gram/m <sup>2</sup> . Density: 240 cm wide. Thickness: 0.55mm. End Use: Window Treatment. Additional Information: Metallised.					
<b>Tested For:</b> Mrs. Conny Pasman Verosol De Kieffe 18 7151 HZ Eibergen, Netherlands	<b>Key Test:</b> NFPA 701-2015 TM#I				225	
			<b>Tel:</b> 011 31 545 46 33 33		<b>Ext:</b>	
			<b>Fax:</b> 011 31 545 46 33 29			
LE:2015 NE:2019 V:01/15 NTR 1/16 PC: 0.5H DL/jd						
TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2015 Edition - Test Method #1						
PRODUCT CONFIGURATION: <input checked="" type="checkbox"/> Single Layer; <input type="checkbox"/> Multi Layer						
RESULTS REPORTED: <input checked="" type="checkbox"/> Initially; <input type="checkbox"/> After 3 dry cleanings; <input type="checkbox"/> After 5 launderings @ 160°F						
RESULTS:						
Specimen #	Afterflame* (seconds)	Flaming Drip (seconds)	Weight Loss (percent)			
1	0	0.0	2.9			
2	0	0.0	24.6			
3	0	0.0	27.2			
4	0	0.0	28.6			
5	0	0.0	23.7			
6	0	8.3	26.6			
7	0	0.0	26.4			
8	0	0.0	28.1			
9	0	5.7	25.7			
10	0	0.0	28.3			
		Mean: 1.4	Mean: 24.2			
STATISTICAL VALUES: SD = 7.7 3 SD = 23.0 Mean + 3 SD = 47.2						
ABBREVIATIONS USED: SD = Standard deviation. NT = Not tested.						
APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 451 g/m <sup>2</sup>						
PRECONDITIONING: <input checked="" type="checkbox"/> 0.5 hr @ 220°F (Standard) <input type="checkbox"/> 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)						
CONVERSION FACTOR: g/m <sup>2</sup> ÷ 28.35 x .835 = oz/yd <sup>2</sup>						
NOTE:						
1. All specimens prepared in the length direction.						
2. See addendum for individual specimen weights.						
(Page 1 of 3)						

File Copy




96-D Allen Boulevard  
 Farmingdale, New York 11735-5626 USA  
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
 e-mail: testing@govmark.com

Received:03/24/2016	Completed:03/24/2016	Letter: Y	BG	P.O.#:	Test Report #:	3-12415-0-
<b>Client's Identification</b>	Style: OmniaScreen. Composition: 75% PVC, 25% Polyester. Weight: 440 gram/m <sup>2</sup> . Density: 240 cm wide. Thickness: 0.55mm. End Use: Window Treatment. Additional Information: Metallised.					
<b>Tested For:</b> Mrs. Conny Pasman Verosol De Kiefe 18 7151 HZ Eibergen, Netherlands	<b>Key Test:</b> NFPA 701-2015 TM#1					225
		<b>Tel:</b> 011 31 545 46 33 33			<b>Ext:</b>	
		<b>Fax:</b> 011 31 545 46 33 29				
REMARKS:						
<input checked="" type="checkbox"/> Flames did not project above the top of the specimen. <input type="checkbox"/> Flames projected above the top of the specimen; Specimen #'s _____ <input type="checkbox"/> Other: _____						
FAILURE CRITERIA: As cited by NFPA 701 - 2015 Edition Test Method #1						
		Flaming Drip		Weight Loss (percent)		
Afterflame	(Mean)	Mean	Individual Specimen			
*	Exceeds 2 seconds	Exceeds 40%	Exceeds Mean + 3 SD**			
CONCLUSION: Based on the Results on page 1 and the above Failure Criteria cited by NFPA 701 - 2015 Edition Test Method #1, the item tested:						
<input checked="" type="checkbox"/> Passes; <input type="checkbox"/> Fails; <input type="checkbox"/> Requires testing of 10 additional specimens i.e. only one individual specimen failure was noted						
* Afterflame is required to be recorded; however, the NFPA document does not factor it into the Failure Criteria reporting requirements. It should be noted that excessive afterflames could be cause for rejection by local fire authorities performing "match" field tests.						
** See "Discussion" on Page 3.						
CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2015 Edition Test Method #1.						
 AUTHORIZED SIGNATURE GOVMARK /gb /sb APR 0 4 2016 <b>Ms. Phyllis Pettit</b>						
(Page 2 of 3)						

File Copy

# OMNIASCREEN

VEROSOL HIGH PERFORMANCE FABRICS



**TEXTSTYLE**



96-D Allen Boulevard  
 Farmingdale, New York 11735-5626 USA  
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
 e-mail: testing@govmark.com

Page 3

Received: 03/24/2016	Completed: 03/24/2016	Letter: Y	BG	P.O.#:	Test Report #:	3-12415-0-
<b>Client's Identification</b>	Style: OmniaScreen. Composition: 75% PVC, 25% Polyester. Weight: 440 gram/m <sup>2</sup> . Density: 240 cm wide. Thickness: 0.55mm. End Use: Window Treatment. Additional Information: Metallised.					
<b>Tested For:</b> Mrs. Conny Pasman	<b>Key Test:</b> NFPA 701-2015 TM#1					225
Verosol De Kieft 18 7151 HZ Eibergen, Netherlands	Tel: 011 31 545 46 33 33		Ext:			
	Fax: 011 31 545 46 33 29					

**\*\* DISCUSSION:**

**Weight Loss - Individual Specimen Failure:**

-----  
 The NFPA 701 document, as written, provides for a statistical calculation which provides for retest and a potential failure if any individual value exceeds the mean by three standard deviations. Govmark is of the opinion that this cannot mathematically occur, i.e. no individual result is mathematically capable of exceeding the mean plus three standard deviations. Therefore, in effect, Govmark is of the opinion that this "individual specimen criteria" has no meaning, since it cannot possibly result in a nonconformance.

(Page 3 of 3)

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from Govmark.

*File Copy*

# OMNIASCREEN

VEROSOL HIGH PERFORMANCE FABRICS



TEXTSTYLE



96D Allen Blvd.  
Farmingdale, NY 11735  
TEL: (516) 293-8944  
FAX: (516) 293-8956

Client Name : Verosol  
Addendum to Test Report # : 3-12415-0  
Test : NFPA 701

<u>Specimen #</u>	<u>Weight Before Test ( g )</u>	<u>Weight After Test ( g )</u>	<u>Percent Weight Loss</u>
1	27.80	27.00	2.9
2	27.60	20.80	24.6
3	27.20	19.80	27.2
4	28.00	20.00	28.6
5	27.80	21.20	23.7
6	27.80	20.40	26.6
7	28.00	20.60	26.4
8	27.80	20.00	28.1
9	28.00	20.80	25.7
10	27.60	19.80	28.3

Mean Percent Weight Loss : 24.2  
Standard Deviation : 7.7  
3 x Standard Deviation : 23.0  
Mean + 3 x Standard Deviation : 47.2

APR 04 2016