



## T Screen Deco 5%

### Specifications

**Product Category:** Decorative  
**Openness Factor:** 5%  
**UV Blockage:** Approximately 95%  
**Fabric Style:** Satin  
**Item #:** 006605

**Composition:** 36% fiberglass / 64% vinyl  
**Standard Packaging:** Rolls of 30 ly (27 lm)  
**Width:** 122" (310 cm)  
**Weight:** 11.89 oz / yd2 (403 g / m2) ± 5%  
**Thickness:** .028" (0.70 mm) ± 5%

### Fenestration Data

			Fabric Properties					Fabric & Glass			
			Thermal			Optical		Commercial		Residential	
Color#	Color Name	Side*	Total Solar			Rv (%)	Tv (%)	SHGC % Improvement		SHGC	
			Rs (%)	As (%)	Ts (%)			Interior	Exterior	Interior	Exterior
00D088	Toffee	street	56	29	15	61	13	45	82	0.38	0.16
		room	38	47	15	42	14	32	76	0.47	0.16
00D064	Cream	street	62	20	18	67	16	47	79	0.35	0.16
		room	51	31	18	55	17	39	74	0.41	0.17
00D065	Cappuccino	street	57	27	16	61	14	45	79	0.37	0.14
		room	38	45	17	39	14	29	76	0.48	0.17
00D067	Mocha	street	52	34	14	56	12	42	82	0.40	0.13
		room	28	57	15	28	13	24	76	0.54	0.16
00D066	Espresso	street	49	38	13	53	12	39	82	0.41	0.13
		room	20	66	14	22	13	21	76	0.57	0.16

\*Room side: identified by the color side; Street side: identified by the white side

The fabric performance tests were conducted in accordance with ASTM E891 & ASTM E903-96: Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory Window 7.3 NFRC certified software. SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm / 1/2" air / 6 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3mm clear glass / 1/2" air / 3mm clear glass. Results for SHGC were obtained using the center of glass. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: [www.mermetusa.com](http://www.mermetusa.com).

#### Fabrication Methods:

Cutting: cold, ultrasonic or crush  
Welding: radio frequency, high frequency, impulse, hot air, wedge

#### Fire Classifications:

NFPA 701-10 TM#1, California U.S. Title 19  
CAN/ULC-S109-03 Small & Large Flame Test

#### Bacterial and Fungal Resistance:

ASTM E2180, ASTM G21

#### Environmental Benefits:

RoHS - Lead Free

#### Acoustical Performance:

NRC: 0.10, SAA: 0.08

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

#### Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

5970 N. Main Street • Cowpens, SC 29330

Sales Department: Ph (866) 902-9647

[info@mermetusa.com](mailto:info@mermetusa.com)



Specifications

Item Number	1% 008501   3% 008503   5% 008505		
Product Category	Conventional		
Fabric Style	Rib Weave		
Openness Factor	1%, 3% & 5%		
Composition	36% Fiberglass   64% Vinyl		
UV Blockage	Approximately 95% - 99%		
Standard Packaging	Rolls of 30 ly (27 lm)		
Width	78 in (200 cm), 98 in (250 cm), 122 in (310 cm)		
Weight	1% 13.12 oz/yd² (445 g/m²)±5%	3% 12.27 oz/yd² (432 g/m²)±5%	5% 11.3 oz/yd² (384 g/m²)±5%
Thickness	1% .022 in (0.56 mm)±5%	3% .022 in (0.55 mm)±5%	5% .022 in (0.55 mm)±5%

Classifications

Fire Classifications

NFPA 701-10 TM#1, California U.S. Title 19,  
CAN/ULC-S109-03 Small & Large Flame Test  
ASTM E2180, ASTM G21

Bacterial & Fungal Resistance

Environment

RoHS - Lead Free, GREENGUARD Gold

Acoustical Performance

1% NRC: 0.50, SAA: 0.47 | 3% NRC: 0.35, SAA: 0.33 | 5% NRC: 0.10, SAA: 0.12

Fabrication

**Cutting:** Cold, Ultrasonic or Crush | **Welding:** Radio Frequency, High Frequency, Impulse, Hot Air or Wedge  
We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabric specifications.

M Screen™

ITEM      COLOR

030071	Charcoal/Apricot
002002	White/White
002007	White/Pearl
007020	Pearl/Linen
007007	Pearl/Pearl
030001	Charcoal/Grey
030030	Charcoal/Charcoal
002022	White/Stone
002020	White/Linen
020022	Linen/Stone
00M166	Linen/Sable-Cocoa
030010	Charcoal/Sable
030061	Charcoal/Cocoa

F A B R I C															F A B R I C + G L A S S														
thermal Total Solar									optical						commercial SHGC % Improvement						residential SHGC								
Rs   %			As   %			Ts   %			Rv   %			Tv   %			Interior			Exterior			Interior			Exterior					
1	3	5	1	3	5	1	3	5	1	3	5	1	3	5	1	3	5	1	3	5	1	3	5	1	3	5			
11	13	13	86	82	80	3	5	7	11	14	13	2	5	7	18	18	16	82	84	84	0.55	0.59	0.60	0.11	0.11	0.11			
76	71	71	9	11	10	15	18	19	81	76	75	12	16	16	63	55	55	82	76	76	0.24	0.29	0.30	0.13	0.16	0.16			
59	54	52	32	36	33	9	10	15	64	58	56	7	8	12	50	45	42	84	84	79	0.32	0.37	0.40	0.10	0.11	0.14			
36	40	39	56	49	49	8	11	12	38	42	41	5	8	9	34	34	32	82	84	82	0.44	0.46	0.47	0.12	0.12	0.13			
32	34	33	63	59	57	5	7	10	34	36	35	4	5	7	26	29	29	84	87	84	0.45	0.48	0.50	0.11	0.10	0.12			
7	8	8	91	90	86	2	2	6	7	8	8	2	2	5	18	16	13	82	87	84	0.56	0.61	0.63	0.12	0.09	0.11			
4	4	4	95	93	93	1	3	3	4	4	4	1	3	3	16	13	11	82	84	87	0.57	0.63	0.64	0.11	0.10	0.09			
67	62	61	15	17	18	18	21	21	71	66	65	16	18	18	55	47	47	76	74	74	0.30	0.35	0.36	0.16	0.18	0.18			
67	64	61	18	21	20	15	15	19	72	67	64	12	11	15	55	50	47	79	82	79	0.29	0.33	0.36	0.14	0.13	0.16			
50	51	50	29	28	28	21	21	22	53	53	52	18	16	18	42	39	37	71	76	74	0.39	0.41	0.42	0.19	0.18	0.19			
39	35	36	50	56	52	11	9	12	41	37	37	9	7	10	37	29	29	79	84	82	0.43	0.48	0.49	0.14	0.11	0.13			
10	12	13	87	84	81	3	4	6	10	13	13	2	4	5	18	18	16	82	84	84	0.55	0.59	0.60	0.12	0.10	0.11			
5	5	5	93	92	90	2	3	5	5	5	5	2	3	4	16	13	13	82	84	84	0.57	0.62	0.64	0.12	0.10	0.10			

Warranty

5 Year Exterior & 10 Year Interior

Care & Handling

Remove dust with a vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or soft brush dipped in soapy water using a mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

The fabric performance tests were conducted in accordance with ASTM E891 & ASTM E903-96: Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory Window 7.3 NFRC certified software. SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm | 1/2" air | 6 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3mm clear glass | 1/2" air | 3mm clear glass. Results for SHGC were obtained using the center of glass. Acoustical performance was tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at [www.mermetusa.com](http://www.mermetusa.com).

Mermet Corporation  
5970 N. Main Street ■ Cowpens, SC 29330  
Ph 1.866.902.9647 ■ [info@mermetusa.com](mailto:info@mermetusa.com)

[mermetusa.com](http://mermetusa.com)



[www.shadesbymatiss.com](http://www.shadesbymatiss.com) | T. 800 493 2040 | email: [info@shadesbymatiss.com](mailto:info@shadesbymatiss.com)