



T Screen Deco 1%

Specifications

Product Category: Decorative
Openness Factor: 1%
UV Blockage: Approximately 99%
Fabric Style: Satin
Item #: 006601

Composition: 36% fiberglass / 64% vinyl
Standard Packaging: Rolls of 30 ly (27 lm)
Width: 122" (310 cm)
Weight: 13.76 oz / yd2 (467 g / m2) ± 5%
Thickness: 0.028" (0.72 mm) ± 5%

Fenestration Data

Color#	Color Name	Side*	Fabric Properties					Fabric & Glass			
			Thermal			Optical		Commercial		Residential	
			Total Solar			Rv (%)	Tv (%)	SHGC % Improvement		SHGC	
Rs (%)	As (%)	Ts (%)	Interior	Exterior	Interior			Exterior			
00D088	Toffee	street	64	28	8	69	7	55	87	0.29	0.09
		room	38	53	9	43	8	37	79	0.43	0.13
00D064	Cream	street	68	21	11	73	10	58	84	0.28	0.11
		room	54	34	12	59	11	47	79	0.35	0.14
00D065	Cappuccino	street	65	26	9	69	8	55	87	0.29	0.10
		room	41	48	11	44	9	37	79	0.42	0.14
00D067	Mocha	street	60	33	7	64	6	53	87	0.31	0.09
		room	27	64	9	27	7	29	79	0.49	0.14
00D066	Espresso	street	58	36	6	62	5	50	89	0.32	0.08
		room	20	73	7	21	6	24	79	0.51	0.13

*Room side: identified by the color side; Street side: identified by the white side

The fabric performance tests were conducted in accordance with ASTM E891 & ASTM E903-96: Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory Window 7.3 NFRC certified software. SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm / 1/2" air / 6 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3mm clear glass / 1/2" air / 3mm clear glass. Results for SHGC were obtained using the center of glass. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: www.mermetusa.com.

Fabrication Methods:

Cutting: cold, ultrasonic or crush
 Welding: radio frequency, high frequency, impulse, hot air, wedge

Fire Classifications:

NFPA 701-10 TM#1, California U.S. Title 19
 CAN/ULC-S109-03 Small Flame Test

Environmental Benefits:

RoHS - Lead Free

Bacterial and Fungal Resistance:

ASTM E2180, ASTM G21

Acoustical Performance:

NRC: 0.10, SAA: 0.11

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

5970 N. Main Street • Cowpens, SC 29330

Sales Department: Ph (866) 902-9647

info@mermetusa.com



Specifications

Item Number	1% 008501 3% 008503 5% 008505
Product Category	Conventional
Fabric Style	Rib Weave
Openness Factor	1%, 3% & 5%
Composition	36% Fiberglass 64% Vinyl
UV Blockage	Approximately 95% - 99%
Standard Packaging	Rolls of 30 ly (27 lm)
Width	78 in (200 cm), 98 in (250 cm), 122 in (310 cm)
Weight	1% 13.12 oz/yd ² (445 g/m ²)±5% 3% 12.27 oz/yd ² (432 g/m ²)±5% 5% 11.3 oz/yd ² (384 g/m ²)±5%
Thickness	1% .022 in (0.56 mm)±5% 3% .022 in (0.55 mm)±5% 5% .022 in (0.55 mm)±5%

Classifications

Fire Classifications	NFPA 701-10 TM#1, California U.S. Title 19, CAN/ULC-S109-03 Small & Large Flame Test
Bacterial & Fungal Resistance	ASTM E2180, ASTM G21
Environment	RoHS - Lead Free, GREENGUARD Gold
Acoustical Performance	1% NRC: 0.50, SAA: 0.47 3% NRC: 0.35, SAA: 0.33 5% NRC: 0.10, SAA: 0.12

Fabrication

Cutting: Cold, Ultrasonic or Crush | **Welding:** Radio Frequency, High Frequency, Impulse, Hot Air or Wedge
We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabric specifications.

M Screen™

ITEM COLOR

030071	Charcoal/Apricot
002002	White/White
002007	White/Pearl
007020	Pearl/Linen
007007	Pearl/Pearl
030001	Charcoal/Grey
030030	Charcoal/Charcoal
002022	White/Stone
002020	White/Linen
020022	Linen/Stone
00M166	Linen/Sable-Cocoa
030010	Charcoal/Sable
030061	Charcoal/Cocoa

F A B R I C															F A B R I C + G L A S S																	
thermal Total Solar									optical						commercial SHGC % Improvement						residential SHGC											
Rs %			As %			Ts %			Rv %		Tv %				Interior			Exterior			Interior			Exterior								
1	3	5	1	3	5	1	3	5	1	3	5	1	3	5	1	3	5	1	3	5	1	3	5	1	3	5	1	3	5	1	3	5
11	13	13	86	82	80	3	5	7	11	14	13	2	5	7	18	18	16	82	84	84	0.55	0.59	0.60	0.11	0.11	0.11						
76	71	71	9	11	10	15	18	19	81	76	75	12	16	16	63	55	55	82	76	76	0.24	0.29	0.30	0.13	0.16	0.16						
59	54	52	32	36	33	9	10	15	64	58	56	7	8	12	50	45	42	84	84	79	0.32	0.37	0.40	0.10	0.11	0.14						
36	40	39	56	49	49	8	11	12	38	42	41	5	8	9	34	34	32	82	84	82	0.44	0.46	0.47	0.12	0.12	0.13						
32	34	33	63	59	57	5	7	10	34	36	35	4	5	7	26	29	29	84	87	84	0.45	0.48	0.50	0.11	0.10	0.12						
7	8	8	91	90	86	2	2	6	7	8	8	2	2	5	18	16	13	82	87	84	0.56	0.61	0.63	0.12	0.09	0.11						
4	4	4	95	93	93	1	3	3	4	4	4	1	3	3	16	13	11	82	84	87	0.57	0.63	0.64	0.11	0.10	0.09						
67	62	61	15	17	18	18	21	21	71	66	65	16	18	18	55	47	47	76	74	74	0.30	0.35	0.36	0.16	0.18	0.18						
67	64	61	18	21	20	15	15	19	72	67	64	12	11	15	55	50	47	79	82	79	0.29	0.33	0.36	0.14	0.13	0.16						
50	51	50	29	28	28	21	21	22	53	53	52	18	16	18	42	39	37	71	76	74	0.39	0.41	0.42	0.19	0.18	0.19						
39	35	36	50	56	52	11	9	12	41	37	37	9	7	10	37	29	29	79	84	82	0.43	0.48	0.49	0.14	0.11	0.13						
10	12	13	87	84	81	3	4	6	10	13	13	2	4	5	18	18	16	82	84	84	0.55	0.59	0.60	0.12	0.10	0.11						
5	5	5	93	92	90	2	3	5	5	5	5	2	3	4	16	13	13	82	84	84	0.57	0.62	0.64	0.12	0.10	0.10						

Warranty

5 Year Exterior & 10 Year Interior

Care & Handling

Remove dust with a vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or soft brush dipped in soapy water using a mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

The fabric performance tests were conducted in accordance with ASTM E891 & ASTM E903-96: Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory Window 7.3 NFRC certified software. SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm | 1/2" air | 6 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3mm clear glass | 1/2" air | 3mm clear glass. Results for SHGC were obtained using the center of glass. Acoustical performance was tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at www.mermetusa.com.

Mermet Corporation
 5970 N. Main Street ■ Cowpens, SC 29330
 Ph 1.866.902.9647 ■ info@mermetusa.com

mermetusa.com

