

E Screen 10%

Specifications

Product Category: Conventional
Openness Factor: 10%
UV Blockage: Approximately 90%
Fabric Style: Basketweave
Item #: 007510



Composition: 36% fiberglass / 64% vinyl
Standard Packaging: Rolls of 30 ly (27 lm)
Width: 78" (200 cm), 98" (250 cm), 122" (310 cm)
Weight: 10.3 oz / yd² (350g / m²) ± 5%
Thickness: .020" (0.52 mm) ± 5%

Fenestration Data

		Fabric Properties					Fabric & Glass			
		Thermal			Optical		Commercial		Residential	
Color#	Color Name	Total Solar			Rv (%)	Tv (%)	SHGC % Improvement		SHGC	
		Rs (%)	As (%)	Ts (%)			Interior	Exterior	Interior	Exterior
030001	Charcoal/Grey	8	80	12	8	11	11	82	0.65	0.14
002002	White/White	66	9	25	70	22	50	71	0.35	0.21
002020	White/Linen	58	17	25	62	22	42	71	0.39	0.21
002007	White/Pearl	50	30	20	54	18	37	74	0.43	0.18
007020	Pearl/Linen	35	46	19	37	17	32	76	0.48	0.19
007007	Pearl/Pearl	30	54	16	31	14	26	76	0.50	0.17
007001	Pearl/Grey	26	58	16	26	14	24	74	0.52	0.17
00M122	Charcoal/Grey-Stone	10	79	11	11	11	16	76	0.58	0.16
030030	Charcoal/Charcoal	3	85	12	4	12	8	79	0.67	0.14
030061	Charcoal/Cocoa	5	84	11	5	11	11	82	0.66	0.13
030071	Charcoal/Apricot	14	72	14	14	13	16	79	0.62	0.15

The fabric performance tests were conducted in accordance with ASTM E891 & ASTM E903-96: Total Solar Transmittance (Ts), Total Solar Reflectance (Rs), Total Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory Window 7.3 NFRC certified software. SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm / 1/2" air / 6 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3mm clear glass / 1/2" air / 3mm clear glass. Results for SHGC were obtained using the center of glass. Acoustical performance was tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: www.mermetusa.com.

Fabrication Methods:

Cutting: cold, ultrasonic or crush
Welding: radio frequency, high frequency, impulse, hot air, wedge

Fire Classifications:

NFPA 701-10 TM#1, California U.S. Title 19
CAN/ULC-S109-03 Small & Large Flame Test

Bacterial and Fungal Resistance:

ASTM E2180, ASTM G21

Environmental Benefits:

RoHS - Lead Free

Acoustical Performance:

NRC: 0.05, SAA: 0.06

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

5970 N. Main Street • Cowpens, SC 29330

Sales Department: Ph (866) 902-9647

info@mermetusa.com

